










## HOME COUNTIES PLAINS CONSTRUCTION SPECIFICATION

	<b>CONSTRUCTION</b>		<b>42oz</b>	<b>50oz</b>
	MACHINE GAUGE		1/10th Gauge	1/10th Gauge
	PILE HEIGHT	ISO 1766	7 mm	8 mm
	TUFT DENSITY	ISO 1763	155,000 tufts/m <sup>2</sup>	170,500 tufts/m <sup>2</sup>
	PILE WEIGHT		1,423 gms/m <sup>2</sup>	1,695 gms/m <sup>2</sup>
			42 oz/yd <sup>2</sup>	50 oz/yd <sup>2</sup>
	TOTAL CARPET WEIGHT	ISO 8543	2,203 gms/m <sup>2</sup>	2,475 gms/m <sup>2</sup>
	CARPET THICKNESS	ISO 1765	9.9 mm	10.9mm
	WIDTH		4 & 5 metre	4 & 5 metre
	<b>COMPOSITION</b>			
	PILE CONTENT	ISO 1833	80% Wool 10% Polypropylene 10% Tuftbond	80% Wool 10% Polypropylene 10% Tuftbond
	PRIMARY BACKING		Woven Polypropylene	Woven Polypropylene
	SECONDARY BACKING		Woven Secondary	Woven Secondary
 EHD	<b>PERFORMANCE</b>			
	SUITABILITY		Extra Heavy Domestic	Extra Heavy Domestic / Medium Contract
	WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 21,500 Rubs	Exceeds 50,000 Rubs
	STATIC LOADING	ISO 3416	31.5% Thickness loss after 24 hrs recovery	25.5% Thickness loss after 24 hrs recovery
	DYNAMIC LOADING	ISO 2094	27.9% Thickness loss after 1,000 impacts	22.5% Thickness loss after 1,000 impacts
	TUFT ANCHORAGE	ISO 4919	Above 1 kg	Above 1 kg
 MC				
	<b>COLOUR FASTNESS</b>			
	LIGHT FASTNESS	ISO 105-B02	4/5 on all colours	4/5 on all colours
	WET FASTNESS	ISO 105-E01	4/5 on all colours	4/5 on all colours
	SHAMPOO FASTNESS	BS 1006:UK-TB	4/5 on all colours	4/5 on all colours
	<b>THERMAL VALUE</b>			
	TOG VALUE	ISO 5085-1	1.4 Tog	1.5 Tog
	THERMAL RESISTANCE		0.14 m <sup>2</sup> k/w	0.15 m <sup>2</sup> k/w
	<b>FLAMMABILITY</b>	<b>CE</b>		
	CE MARK RATING		Dfl,S1	Dfl,S1
	HOT METAL NUT TEST	BS4790	Pass	Pass
	METHENAMINE PILL TEST	ISO 6925	Pass - Low radius of ignition	Pass - Low radius of ignition
	<b>CHEMICAL IMPACT</b>	<b>CE</b>		
	FORMALDEHYDE		E1	E1
	REACH CERTIFICATE		Compliant	Compliant
	<b>BIOLOGICAL ATTACK</b>			
	moth / INSECT RESISTANT		Eulan Treated	Eulan Treated

### GENERAL INFORMATION

**Installation** - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type. For quantity orders requiring colour matching, please state at time of ordering.

**Maintenance** - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear. These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

**Matching** - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

**Important** - Minimum order length is 1.5 metres.

February 2014



**GREENWOOD & COOPE LTD.** BROOKHOUSE MILL, GREENMOUNT, BURY, LANCASHIRE BL8 4HR

TEL: 01204 881234 FAX: 01204 887722

E-MAIL: info@cormarcarpets.co.uk WEBSITE: www.cormarcarpets.co.uk

