










MALABAR TWO-FOLD CONSTRUCTION SPECIFICATION

	<p>CONSTRUCTION</p> <table border="0"> <tr> <td>MACHINE GAUGE</td> <td></td> <td>5/32nd Loop Pile</td> </tr> <tr> <td>PILE HEIGHT</td> <td>ISO 1766</td> <td>5 mm</td> </tr> <tr> <td>TUFT DENSITY</td> <td>ISO 1763</td> <td>89,279 loops/m²</td> </tr> <tr> <td>PILE WEIGHT</td> <td></td> <td>1,017 gms/m²</td> </tr> <tr> <td></td> <td></td> <td>30 oz/yd²</td> </tr> <tr> <td>TOTAL CARPET WEIGHT</td> <td>ISO 8543</td> <td>1,954 gms/m²</td> </tr> <tr> <td>CARPET THICKNESS</td> <td>ISO 1765</td> <td>7.9 mm</td> </tr> <tr> <td>WIDTH</td> <td></td> <td>4 & 5 metre</td> </tr> </table>	MACHINE GAUGE		5/32nd Loop Pile	PILE HEIGHT	ISO 1766	5 mm	TUFT DENSITY	ISO 1763	89,279 loops/m ²	PILE WEIGHT		1,017 gms/m ²			30 oz/yd ²	TOTAL CARPET WEIGHT	ISO 8543	1,954 gms/m ²	CARPET THICKNESS	ISO 1765	7.9 mm	WIDTH		4 & 5 metre
MACHINE GAUGE		5/32nd Loop Pile																							
PILE HEIGHT	ISO 1766	5 mm																							
TUFT DENSITY	ISO 1763	89,279 loops/m ²																							
PILE WEIGHT		1,017 gms/m ²																							
		30 oz/yd ²																							
TOTAL CARPET WEIGHT	ISO 8543	1,954 gms/m ²																							
CARPET THICKNESS	ISO 1765	7.9 mm																							
WIDTH		4 & 5 metre																							
	<p>COMPOSITION</p> <table border="0"> <tr> <td>PILE CONTENT</td> <td>ISO 1833</td> <td>100% Wool</td> </tr> <tr> <td>PRIMARY BACKING</td> <td></td> <td>Woven Polypropylene</td> </tr> <tr> <td>SECONDARY BACKING</td> <td></td> <td>Woven Secondary</td> </tr> </table>	PILE CONTENT	ISO 1833	100% Wool	PRIMARY BACKING		Woven Polypropylene	SECONDARY BACKING		Woven Secondary															
PILE CONTENT	ISO 1833	100% Wool																							
PRIMARY BACKING		Woven Polypropylene																							
SECONDARY BACKING		Woven Secondary																							
	<p>PERFORMANCE</p> <table border="0"> <tr> <td>SUITABILITY</td> <td></td> <td>Extra Heavy Domestic / Medium Contract</td> </tr> <tr> <td>WIRA ABRASION TEST</td> <td>PD 6527:Clause 17</td> <td>Exceeds 13,200 Rubs</td> </tr> <tr> <td>STATIC LOADING</td> <td>ISO 3416</td> <td>28.6% Thickness loss after 24 hrs recovery</td> </tr> <tr> <td>DYNAMIC LOADING</td> <td>ISO 2094</td> <td>26.5% Thickness loss after 1,000 impacts</td> </tr> <tr> <td>TUFT ANCHORAGE</td> <td>ISO 4919</td> <td>Above 1kg</td> </tr> </table>	SUITABILITY		Extra Heavy Domestic / Medium Contract	WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 13,200 Rubs	STATIC LOADING	ISO 3416	28.6% Thickness loss after 24 hrs recovery	DYNAMIC LOADING	ISO 2094	26.5% Thickness loss after 1,000 impacts	TUFT ANCHORAGE	ISO 4919	Above 1kg									
SUITABILITY		Extra Heavy Domestic / Medium Contract																							
WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 13,200 Rubs																							
STATIC LOADING	ISO 3416	28.6% Thickness loss after 24 hrs recovery																							
DYNAMIC LOADING	ISO 2094	26.5% Thickness loss after 1,000 impacts																							
TUFT ANCHORAGE	ISO 4919	Above 1kg																							
	<p>COLOUR FASTNESS</p> <table border="0"> <tr> <td>LIGHT FASTNESS</td> <td>ISO 105-B02</td> <td>5/6 on all colours</td> </tr> <tr> <td>WET FASTNESS</td> <td>ISO 105-E01</td> <td>4/5 on all colours</td> </tr> <tr> <td>SHAMPOO FASTNESS</td> <td>BS 1006:UK-TB</td> <td>4/5 on all colours</td> </tr> </table>	LIGHT FASTNESS	ISO 105-B02	5/6 on all colours	WET FASTNESS	ISO 105-E01	4/5 on all colours	SHAMPOO FASTNESS	BS 1006:UK-TB	4/5 on all colours															
LIGHT FASTNESS	ISO 105-B02	5/6 on all colours																							
WET FASTNESS	ISO 105-E01	4/5 on all colours																							
SHAMPOO FASTNESS	BS 1006:UK-TB	4/5 on all colours																							
	<p>THERMAL VALUE</p> <table border="0"> <tr> <td>TOG VALUE</td> <td>ISO 5085-1</td> <td>1.2 Tog</td> </tr> <tr> <td>THERMAL RESISTANCE</td> <td></td> <td>0.12 m² k/w</td> </tr> </table>	TOG VALUE	ISO 5085-1	1.2 Tog	THERMAL RESISTANCE		0.12 m ² k/w																		
TOG VALUE	ISO 5085-1	1.2 Tog																							
THERMAL RESISTANCE		0.12 m ² k/w																							
	<p>FLAMMABILITY CE</p> <table border="0"> <tr> <td>CE MARK RATING</td> <td></td> <td>Cfl, S1</td> </tr> <tr> <td>HOT METAL NUT TEST</td> <td>BS4790</td> <td>Pass - Low radius of ignition</td> </tr> <tr> <td>METHENAMINE PILL TEST</td> <td>ISO 6925</td> <td>Pass</td> </tr> </table>	CE MARK RATING		Cfl, S1	HOT METAL NUT TEST	BS4790	Pass - Low radius of ignition	METHENAMINE PILL TEST	ISO 6925	Pass															
CE MARK RATING		Cfl, S1																							
HOT METAL NUT TEST	BS4790	Pass - Low radius of ignition																							
METHENAMINE PILL TEST	ISO 6925	Pass																							
	<p>CHEMICAL IMPACT CE</p> <table border="0"> <tr> <td>FORMALDEHYDE</td> <td></td> <td>E1</td> </tr> <tr> <td>REACH CERTIFICATE</td> <td></td> <td>Compliant</td> </tr> </table>	FORMALDEHYDE		E1	REACH CERTIFICATE		Compliant																		
FORMALDEHYDE		E1																							
REACH CERTIFICATE		Compliant																							
	<p>BIOLOGICAL ATTACK</p> <table border="0"> <tr> <td>MOTH / INSECT RESISTANT</td> <td></td> <td>Eulan Treated</td> </tr> </table>	MOTH / INSECT RESISTANT		Eulan Treated																					
MOTH / INSECT RESISTANT		Eulan Treated																							
	<p>ANTI STATIC</p> <p>-0.3 kv (Requirement less than +2.0 kv)</p>																								

GENERAL INFORMATION

Installation - In all contract locations an 'all over' stick down method is recommended to BS 5325 (1983). If underlay is required the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - Please note all pile carpets of any fibre type will flatten to some extent in traffic lanes although regular vacuuming will help to allay this. This 'flattening' is a normal reaction to localised traffic in both domestic and contract locations and is not a manufacturing fault, therefore will not be accepted as the basis for any claim. Rubber soled shoes when used constantly in heavy traffic areas can sometimes act abrasively on the surface of the carpet therefore it is recommended that their use is limited. Loop pile carpets should be vacuumed with a cylinder cleaner or suction head only. Occasionally wool may contain traces of the sheep's natural environment. These traces can be easily removed and do not affect the durability of the carpet. Joins in loop pile carpet can sometimes be visible, especially so in patterned loop pile. The use of seaming cement is advisable.

Heather Shades - In manufacturing heather shades several contrasting colours are blended to create a 'heather' yarn. As such random coloured flecks will be apparent in the carpet. These flecks form part of the effect and are not considered the basis for any claim.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 4 & 5 metre widths cannot be guaranteed.

Important - A good quality underlay is always recommended when fitting a new carpet. Minimum order length 1.5 metres.

April 2016



GREENWOOD & COOPE LTD. Brookhouse Mill, Greenmount, Bury, Lancashire BL8 4HR

TEL: 01204 881234 FAX: 01204 887722

E-MAIL: info@cormarcarpets.co.uk WEBSITE: www.cormarcarpets.co.uk

